
Anti-Static Sheet Protector





RoHS and REACH Compliance Statement

None of the RoHS restricted materials or REACH substances of very high concern are intentionally added in manufacturing this product. Ref: Directive 2002/95/EC Article 4.1. and Regulation (EC) No. 1907/2006. See Desco Industries Inc. Limited Warranty at Desco.com.

Per ANSI/ESD S541 section 7.2.2 Resistance of Dissipative Materials "A static dissipative material shall have a surface resistance of greater than or equal to 1.0 x 10^4 ohms but less than 1.0 x 10^11 ohms. Packaging materials that are in intimate contact with devices should be dissipative."

"It should be understood that any object, item, material or person could be a source of static electricity in the work environment. Removal of unnecessary nonconductors, replacing nonconductive materials with dissipative or conductive materials and grounding all conductors are the principle methods of controlling static electricity in the workplace, regardless of the activity." [ESD Handbook ESD TR20:20-2008 section 2.4 Sources of Static Electricity]

DESCO

Description:

Desco's standard weight (3 mil) sheet protector is made from a static dissipative coextruded polyolefin material. The triboelectric charge generation of the material is negligible (tested per EIA-541) to make them safe for use around ESD susceptible items. They are designed for top loading a standard 8.5" x 11" sheet of paper and have a standard 3-hole punch for use with a binder.

Electrical Properties:

 Static Decay:
 < 1.0 sec.</th>
 per FTMS 101C, Method 4046

 Surface Resistance:
 1 x 10^4 < 1 x 10^11 ohms</td>
 per ANSI/ESD STM11.11

Specifications:

Polycarbonate Compatibility: 3,400 PSI @ 73°F

Corrosivity: Negligible per FTMS 101C-3005 Tensile Strength: 2000-3000 PSI per ASTM D-882 Elongation @ Break: 500-800% per ASTM D882 Ball Burst Impact Strength: 20-30 cm/kg per ASTM D-3420 Tear Propagation: per ASTM D-1938 200 grams Modulus of Elasticity: 10.000-15.000 PSI per ASTM D-882A Coefficient of Friction: 0.3 Kinetic, Film to Film per ASTM D-1894

N-Octanoic Acid Free

Has No Measurable Outgassing

Sheet Protectors are hot stamped with:

"Descoindustries.com #07450/16252 ESD Protective"





Inside Dimension Tolerances are -0/+1/4" unless specified
Specifications and procedures subject to change without notice.

STATFREE® SHEET PROTECTOR, STATIC DISSIPATIVE, 3 MIL

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407 PHONE (781) 821-8370 DRAWING NUMBER 07450

April 2012

Baskiville.com Ltd. Tel: 0508 227548